

AD-A188 284

DYNAMIC BEHAVIOR OF FIBER AND PARTICLE REINFORCED  
COMPOSITES(U) COLORADO UNIV AT BOULDER DEPT OF  
MECHANICAL ENGINEERING S K DATTA 28 APR 87

1/1


UNCLASSIFIED

CUMER-1531738 N00014-86-K-0280

F/G 11/4

NL





MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

12

SECURITY CLASSIFICATION OF THIS PAGE

## REPORT DOCUMENTATION PAGE

AD-A180 204		1d. RESTRICTIVE MARKINGS	
		3. DISTRIBUTION/AVAILABILITY OF REPORT Unrestricted	
4. PERFORMING ORGANIZATION REPORT NUMBER(S) 1531738		5. MONITORING ORGANIZATION REPORT NUMBER(S) N00014-86-K-0280	
6a. NAME OF PERFORMING ORGANIZATION University of Colorado, Boulder	6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION Office of Naval Research	
6c. ADDRESS (City, State and ZIP Code) Mechanical Engineering Department Campus Box 427 Boulder, Colorado 80309		7b. ADDRESS (City, State and ZIP Code) 800 N. Quincy Street Arlington, VA 22217	
8a. NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research	8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-86-K-0280	
8c. ADDRESS (City, State and ZIP Code) 800 N. Quincy Street Arlington, VA 22217		10. SOURCE OF FUNDING NOS.	
11. TITLE (Include Security Classification) Dynamic Behavior of Fiber and Particle Reinforced Composites		PROGRAM ELEMENT NO.	TASK NO.
12. PERSONAL AUTHOR(S) Professor Subhendu K. Datta		PROJECT NO.	WORK UNIT NO.
13a. TYPE OF REPORT Annual	13b. TIME COVERED FROM 4/21/86 TO 4/20/87	14. DATE OF REPORT (Yr., Mo., Day) 1987, April 28	
15. PAGE COUNT 11		16. SUPPLEMENTARY NOTATION MAY 11 1987	
17. COSATI CODES		18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB. GR.	
19. ABSTRACT (Continue on reverse if necessary and identify by block number)			
<p>Full anisotropic behavior of fiber reinforced composites has been studied. Comparison of model predictions with available experiments shows excellent agreement. This also allows the determination of anisotropic fiber properties in an inverse fashion. We have also studied the frequency dependence of phase velocities and attenuation in a particle reinforced composite allowing for the effect of non-perfect interfaces. In addition, calculations have been performed for the dispersion of guided waves in laminated anisotropic plates. In this context effect of interface layers has also been studied.</p> <p>Simultaneously we have examined ultrasonic scattering by surface-breaking cracks. In particular, we have studied the effect of crack branches on the ultrasonic signal. Scattering of ultrasonic SH waves by buried canted cracks in a thick plate has also been investigated. Here the results of calculations show excellent agreement with available experiments.</p>			
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS <input type="checkbox"/>		21. ABSTRACT SECURITY CLASSIFICATION	
22a. NAME OF RESPONSIBLE INDIVIDUAL	22b. TELEPHONE NUMBER (Include Area Code)	22c. OFFICE SYMBOL	

DYNAMIC BEHAVIOR OF FIBER AND PARTICLE REINFORCED COMPOSITES

Annual Report  
for the period 4/21/86-4/20/87

Contract number: N00014-86-K-0280

Work Unit number: 4324-774

Scientific Officer: Y. Rajapakse



Accession For	
NTIS GRA&I	
DTIC TAB	
Unannounced	
Justification	
By _____	
Distribution/	
Availability	
Dist	
A1	

### Summary

Full anisotropic behavior of fiber reinforced composites has been studied. Comparison of model predictions with available experiments shows excellent agreement. This also allows the determination of anisotropic fiber properties in an inverse fashion. We have also studied the frequency dependence of phase velocities and attenuation in a particle reinforced composite allowing for the effect of non-perfect interfaces. In addition, calculations have been performed for the dispersion of guided waves in laminated anisotropic plates. In this context effect of interface layers has also been studied.

Simultaneously we have examined ultrasonic scattering by surface-breaking cracks. In particular, we have studied the effect of crack branches on the ultrasonic signal. Scattering of ultrasonic SH waves by buried canted cracks in a thick plate has also been investigated. Here the results of calculations show excellent agreement with available experiments.

#### 1. Ultrasonic determination of mechanical properties of Fiber-reinforced composites

A model has been developed that describes the full anisotropic behavior of uniaxial fiber reinforced composites. Model calculations have been performed for various systems: graphite-epoxy, graphite-aluminum, graphite-magnesium, etc. These results agree well with experiments conducted at the NBS laboratories in Boulder by Dr. H. M. Ledbetter. Theoretical predictions have been used in conjunction with experimental results to inversely calculate graphite fiber elastic properties. This is very useful because not all the elastic constants of graphite fibers are available from the manufacturers. Usually only the Young's modulus information is given. Results of our investigation are reported in [1-3].

#### 2. Dispersion of elastic waves in a particle-reinforced composite

Using a scattering approach we have studied [3-5] the frequency dependence of phase velocities and attenuation in a particle reinforced composite. Effects of thin interface layers between the particles and the matrix have been examined. It is shown that the presence of a thin interface layer through which the elastic properties change continuously from those of the particles to those of the matrix usually decreases both the phase velocities and attenuation of plane longitudinal and shear waves.

#### 3. Guided waves in laminated composite plates

Guided waves in a fiber-reinforced laminated plate are of considerable interest for analyzing its dynamic behavior and for ultrasonic characterization of defects in the plate. This problem is a rather difficult one to analyze by exact analytical techniques. We have developed a stiffness method that preserves the continuity of displacements and tractions at the interfaces between adjacent layers. This method is quite versatile and applies to wave propagation in any direction in the plane of the plate. The technique has been used to study dispersion of guided waves in a laminated isotropic plate with thin interface layers [3,8] as well as in  $0^\circ/90^\circ/0^\circ$  graphite fiber-reinforced epoxy and magnesium plates with or without interface layers [6,7]. It is found that the presence of low-velocity <interface layers decreases significantly the phase velocity as well as the cut-off frequency. This phenomenon can be used to characterize interface layers.

#### 4. Scattering of elastic waves by buried and surface-breaking cracks

This effort is concerned with ultrasonic scattering by cracks in homogeneous and laminated plates. During the past year we have studied [9] diffraction of SH waves by buried canted cracks in a homogeneous plate. Model calculations have been found to agree well with the experiments performed by Mr. R. E. Schramm at the NBS laboratories, Boulder. We have also examined [9-11] scattering of body and surface waves by surface-breaking canted and branched cracks. It is found that cant angle and branches modify ultrasonic signals measurably. This would make it possible to discriminate between these various cracks.

### Cited References

1. S. K. Datta and H. M. Ledbetter, "Ultraonic characterization of Material Properties of Composite Materials," Proceedings of the Tenth U.S. National Congress of Applied Mechanics, ed. J. P. Lamb, the American Society of Mechanical Engineers, New York, 1987, pp. 377-387.
2. S. K. Datta and H. M. Ledbetter, "Ultrasonic-Velocity Studies in Metal-Matrix Composites: Measurements and Modeling," Proceedings, Nondestructive Testing and Evaluation of Advanced Materials and Composites Conference, August 19-21, 1986, U.S. Air Force Academy, Colorado Springs, Colorado.
3. S. K. Datta, H. M. Ledbetter, and A. H. Shah, "Ultrasonic-Velocity Studies of Composite and Heterogeneous Materials," To be presented at the Conference on Acousto-Ultrasonics: Theory and Application, July 12-15, 1987, VPI, Blacksburg, VA; Report CUMER-87-1, University of Colorado, Boulder.
4. S. K., Datta, H. M. Ledbetter, Y. Shindo, and A. H. Shah, "Interface Effects on Attenuation and Phase Velocities in Composites," CUMER-86-3, August 1986, University of Colorado, Boulder.
5. S. K. Datta, H. M. Ledbetter, Y. Shindo, and A. H. Shah, "Interface Effects on Phase Velocity and Attenuation in Metal-Matrix Composites," To appear in the Proceedings of the Review of Progress in Quantitative Nondestructive Evaluation, August 3-8, 1986, La Jolla, CA.
6. S. K. Datta, A. H. Shah, R. L. Bratton, and Y. N. Al-Nassar, "Guided Wave Propagation in Laminated Composite Plates with Low-velocity Interface Layers," to be published.
7. S. K. Datta, A. H. Shah, Y. Al-Nassar, and R. L. Bratton, "Elastic Wave Dispersion in Laminated Composite Plate," to be presented at the Review of Progress in Quantative Nondestructive Evaluation, June 21-36, 1987, Williamsburg, VA.
8. S. K. Datta, A. H. Shah, R. L. Bratton, and Y. Al-Nassar, "Surface and Interface Waves in a Sandwich Plate with Interface Soft Layers," to be presented at the Euromach 226, Nonlinear and other Non-classical Effects in Surface Acoustic Waves, September 2-5, 1987, Nottingham, England.
9. S. K. Datta and A. H. Shah, "Ultrasonic Scattering and Nondestructive Evjaluation of Defects," CUMER-86-5, August 1986, University of Colorado, Boulder; Proceedings, Nondestructive Testing and Evaluation of Advanced Materials and Composites Conference, August 19-21, 1986, U.S. Air Force Academy, Colorado Springs, CO.
10. S. K. Datta and A.H. Shah, "Ultrasonic Scattering by Planar and Non-planar Cracks,," CUMER-86-4, August 1986, University of Colorado, Boulder.
11. A. H. Shah, Y. F. Chin, and S. K. Datta, "Elastic Wave Scattering by Surface-breaking Planar and Non-planar Cracks," to be published in the Journal of Applied Mechanics.

END

6-87

DTIC